

Coronado Stone® is manufactured to meet or exceed specifications for all major code approvals. Independent testing confirms compliance with ICC-ES AC51 for Precast Stone Veneer. Always check your local building codes before installing stone.

MATERIALS:

- Cement ASTM C150
- Sand ASTM C144 or C33
- Aggregate ASTM C33 or C330

TESTING:

- Shear Bond Test Tested in accordance with ASTM C482
Greater than 50 psi
- Water Absorption Tested in accordance with section 3.1.4 & 4.6
of ICC-ES AC51
- Freeze / Thaw Tested in accordance with ASTM C67
Less than 3% mass loss
- Unit Weight Shipping weight is less than 15 lbs. per sq. ft.
Density is determined in accordance with ASTM
C567
- Compressive Strength Tested in accordance with ASTM C39
Greater than 1800 psi
- Tensile Strength Tested in accordance with ASTM C190
- Flexural Strength Tested in accordance with ASTM C348
- Thermal Resistance Tested in accordance with ASTM C518-15
R-value: 0.36 (ft²-F-hr)/BTU at 1" thickness.
Average thickness may vary on different
Coronado Stone veneer products and the
R-value will vary accordingly.

